

**Amendments to the Specification:**

Please replace paragraph 61, with the following amended paragraph:

[61] The innermost polystyrenic layer may include from 70% to 90% polystyrenic polymer by weight of the layer. In Examples 1-4, the polystyrene represented 70% to 75% by weight of the innermost polystyrenic layer in each example. Examples 1 and 2 used a blend of two polystyrenes, namely Nova Chemicals Grade 1600 and Grade 3900. It was found that little difference in performance was attributable to using the blended polystyrene vs. a single polystyrene resin. Examples 3 and 4 used the single polystyrene Nova Chemicals Grade 1600.